14-CLASSIC-190-NATOLIE-DG



lalegno =

Size Board	
LENGTH	1900 mm
WIDTH	190 mm
TOTAL THICKNESS	14 mm
THICKNESS TOP LAYER	3 mm
PLANK QUANTITY	Min. 7 Pl. x 1900 mm

Size Pack		Size Pallet	
PACK LENGTH	1910 mm	LENGTH PALLET	1930 mm
PACK WIDTH	200 mm	WIDTH PALLET	1000 mm
PACK THICKNESS	120 mm	HEIGHT PALLET	1080 mm
PACK WEIGHT	24 kg	WEIGHT PALLET	975 kg
LAYERS/PACK	8	PACKS/PALLET	40
M ² /PACK	2.89 m ²	M ² /PALLET	115.6 m ²

Characteristics

Top layer

WOOD SPECIES	Oak
LATIN NAME	Quercus Robur
GRADE	CLASSIC
CONSTRUCTION	3-layer
THICKNESS TOP LAYER	3 mm
STRIPS	1 strip
CUTTING METHOD	Sawn veneer
BEVEL	Two long sides (0,75 mm)
COLOUR FINISH	Smoked Natural oiled
SURFACE STRUCTURE	Smooth

Composition of the support

SUPPORT TYPE Poplar support and backing	
WOOD SPECIES SUPPORT Poplar	
SUPPORT CONSTRUCTION 2-layer (Support, balancer)	
TOTAL THICKNESS SUPPORT 11 mm	
ADHESION Crosswise (Casco)	

Installation

SYSTEM

Tongue and groove system



APPLICATIONS

Light household use Moderate commercial use Normal commercial use Normal household use Intensive commercial use

UNDERFLOOR HEATING

Yes RESANDABLE

Resandable

© This fact sheet was written by Labeco BVBA, Warandestraat 37-39, B-9810 NAZARETH. Text, photographs, drawings, tables , graphs should in no way be distributed , used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables , graphs used in this sheet are intended only as illustrations. No rights can be derived from them.



14-CLASSIC-190-NATOLIE-DG

Certification	This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)
	 Formaldehyde emission, determined according to standard EN 13183-1: E1 Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60% Width Shrinkage, complies with standard EN 13647 Reaction to fire, determined according to standard EN 13501-1: Dfl-S1 Does not contain any PCP (pentachlorophenol)

Technical specifications

- Hardness: N / mm ² (Birnell Hardness) 3.40

- Thermal conductivity: λ 14, 00 (W / (mk)) R = 0.11 m² K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)

© This fact sheet was written by Labeco BVBA, Warandestraat 37-39, B-9810 NAZARETH. Text, photographs, drawings, tables, graphs should in no way be distributed, used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables, graphs used in this sheet are intended only as illustrations. No rights can be derived from them.

LabeCo bvba Sprietestraat 326 B-8792 DESSELGEM Tel. +32 56 540 168 e-mail: <u>info@lalegno.be</u> URL: <u>www.lalegno.be</u>

Declaration of performance Nr. RV-130199

Labeco BVBA herewith declares that the product described below is conform with the provisions of the Construction Products Regulation (EU) No 305/2011 if installed according to the installation instructions provided in the packaging. More information on the technical aspects and use of this product can be found on the website <u>www.lalegno.be</u>

Unique identification	14-CLASSIC-190-N	ATOLIE-DG	
Labeling	See CE-label and marking on the packaging		
Use	Wooden flooring – multilayer parquet branded Lalegno – floor covering for indoor use.		
Name and coordinates of the importer	LABECO BVBA Sprietestraat 326 8792 DESSELGEM BELGIUM		
Name and contact address Agent	none		
Activity of the notified certification body as required by the harmonized standard	In accordance with the requirements of EN 14342:2005+A1:2008		
European Technical Assessment	Inapplicable	Inapplicable	
Declared performance			
Essential characteristics	Performance	European Assessment Document	
Reaction to fire	Dfl – s1	EN 13501-1 – EN 14342, Chapter 4, Table 1	
Formaldehyde emission	E1	EN 717-1	
Pentachlorophenol (PCP) content	< 5 ppm	EN 14342:2005+A1:2008, Chapter 4.3	
Breaking strenght	NPD	EN 14342:2005+A1:2008	
Slipperiness	NPD	EN 14342:2005+A1:2008	
Thermal conductivity	Λ 14,00(W/(mk)) R= 0,11 m² k/w	EN 14342:2005+A1:2008, Chapter 4, Table 2	
Biological durability	Class 1	EN 14342:2005+A1:2008 – Chapter 6.3.4.8	
This statement has been prepared	according to method	4 of appendix ZA.2 to norm EN 14342:2005+A1:200	

The performance of the described product is consistent with the declared performance. This declaration of performance is issued under the sole responsibility of the mentioned importer.

Waregem, 25/06/2017

Signed: J. Labeeuw
t
Managing director